

D

COARSE AGGREGATES.

(REV 6-8-05)

SUBARTICLE 901-4.2 (Page 774) is deleted and the following substituted:

901-4.2 Lightweight Coarse Aggregate for Structural Concrete: The requirements of 901-4.1 are modified as follows:

Aggregates shall not be produced from pumice and scoria.

Los Angeles Abrasion (FM 1-T 096, Section 12) shall be 45%, maximum.

Gradation shall meet the requirements of AASHTO M 195 for 3/4 inch [19 mm], 1/2 inch [13 mm] and 3/8 inch [10 mm].

R

ARTICLE 901-5 (Page 774) is deleted and the following substituted:

901-5 Reclaimed Portland Cement Concrete.

The reclaimed portland cement concrete shall be from a source which was produced and placed in accordance with applicable Specifications. This material may be used as the coarse aggregate in Nonstructural Concrete applications. The material shall be crushed and processed to provide a clean, hard, durable aggregate having a uniform gradation free from adherent coatings, metals, organic matter, base material, joint fillers, and bituminous materials.

The Contractor's (Producer's) crushing operation shall produce an aggregate meeting the applicable gradation requirements. The physical property requirements of 901-1.3 for Soundness shall not apply and the maximum loss as determined by the Los Angeles Abrasion (FM 1-T 096) is changed to 50.

The sources of reclaimed portland cement concrete will be treated as a mine and subject to the requirement of Section 6.

A

F

T