

EXPECTED IMPLEMENTATION JANUARY 2009

288 CEMENT TREATED PERMEABLE BASE.
(REV 6-10-08) (FA 6-20-08) (1-09)

ARTICLE 288-7 (Page 228) is deleted and the following substituted:

288-7 Sampling and Testing.

The Engineer will take random samples of the Cement Treated Permeable Base at the point of placement in accordance with FM 5-530 to determine the unit weight. Cement Treated Permeable Base not within ± 3 lbs/ft³ of the unit weight of the approved mix design will be rejected.

Remove, and replace all rejected Cement Treated Permeable Base at no cost to the Department.

D

R

A

F

T