



Florida Department of Transportation

CHARLIE CRIST
GOVERNOR

605 Suwannee Street
Tallahassee, FL 32399-0450

STEPHANIE KOPELOUSOS
SECRETARY

December 2, 2010

Monica Gourdine
Program Operations Engineer
Federal Highway Administration
545 John Knox Road, Suite 200
Tallahassee, Florida 32303

Re: Office of Design, Specifications
Section **200**
Proposed Specification: **2000702 Rock Base.**

Dear Ms. Gourdine:

We are submitting, for your approval, two copies of the above referenced Supplemental Specification.

These changes were proposed by Ben Watson of the State Materials Office to specify the minimum density requirements for shoulder only areas and bike/shared use paths.

Please review and transmit your comments, if any, within two weeks. Comments should be sent via email to SP965RP or rudy.powell@dot.state.fl.us.

If you have any questions relating to this specification change, please call Rudy Powell, State Specifications Engineer at 414-4280.

Sincerely,

Rudy Powell, Jr., P.E.
State Specifications Engineer

RP/dt

Attachment

cc: Gregory Jones, Chief Civil Litigation
Florida Transportation Builders' Assoc.
State Construction Engineer

ROCK BASE.**(REV ~~109-1221~~-10)**

SUBARTICLE 200-7.2.1 (Page 208) is deleted and the following substituted:

200-7.2.1 Density: Within the entire limits of the width and depth of the base, obtain a minimum density in any LOT of 98% of modified Proctor maximum density as determined by FM 1-T 180, Method D. *For shoulder only areas and bike/shared use paths, obtain a minimum density of* ~~Compact the base of any LOT of shoulder pavement to not less than~~ 95% of the modified Proctor maximum density as determined by FM 1-T 180, Method D.

ROCK BASE.**(REV 10-12-10)**

SUBARTICLE 200-7.2.1 (Page 208) is deleted and the following substituted:

200-7.2.1 Density: Within the entire limits of the width and depth of the base, obtain a minimum density in any LOT of 98% of modified Proctor maximum density as determined by FM 1-T 180, Method D. For shoulder only areas and bike/shared use paths, obtain a minimum density of 95% of the modified Proctor maximum density as determined by FM 1-T 180, Method D.