

# EXPECTED IMPLEMENTATION JULY 2016

D

## 911 BASE AND STABILIZED BASE MATERIALS. (REV 11-3-15) (FA 1-11-16) (7-16)

SUBARTICLE 911-3.1 is deleted and the following substituted:

**911-3.1 Limerock Bearing Ratio (LBR):** Materials shall meet the requirements in Table 911-1 in accordance with FM 5-515:

R

Table 911-1 Limerock Bearing Ratio (LBR)	
Material	Requirement
Limerock	Average Results per LOT - 100, minimum Individual Results - 90, minimum
Shell	
Shell-Rock	
Cemented Coquina Shell	
RCA	Individual Result - 150, minimum

A

F

T