
**Florida Method of Test
for
MATERIALS FINER THAN 75 μ m (No. 200) SIEVE IN MINERAL
AGGREGATE BY WASHING**

Designation: FM 1-T 011

FM 1-T 011 is identical to AASHTO T 11 with the following provisions:

1. Add section 1.2.1 stating, "The total amount of material finer than 75 μ m (No. 200) sieve is the minus 200 material lost by decantation of wash water via this method plus the minus 200 material obtained by dry sieving the undecanted residue via AASHTO T 27."
2. Replace "T 2" in Section 2.1 with FM 1-T 002.

Replace "T 248" in Section 2.1 with FM 1-T 248.
3. Add the following after Section 5.3: The volume of the pan shall be at least two times the volume of the wash sample.
4. Replace Note 1 with the following; "This method does not approve the use of a mechanical washing apparatus".
5. Replace "T 2" in Section 6.1 with FM 1-T 002 and replace "T 248" in Section 6.2 with FM 1-T 248.
6. Delete Section 7 and Section 8.1-8.4 and note 3 (keep notes 4 and 5).
7. Add the following after Section 9.2, sentence 4;

Hand mix the sample with sifting and swirling action sufficient to result in complete separation of all particles finer than the 75 μ m (No. 200) sieve from the coarser particles. The intent of this method is to eliminate the generation of additional fine material by deliberately crushing or grinding the aggregate."
8. Add the following after the last sentence in Section 9.3:
"but not more than 20 wash cycles."
9. Change sentence two in section 8.5 to
"determine the weight to the nearest 1g or 0.1% of the sample weight, whichever is greater."

10. Delete Section 11.1 and replace it with “Report the total percentage of material finer than the 75- μm (No 200) sieve to the nearest 0.01percent”.