

## Pavement Composition Data Sheet

Date: March 22, 2012

Milling Depth : 3.00 in.

Page: 1

F. P. N. : 429120-1-52-01	S.R. No.: 84	<u>Notes</u>
F. A. P. No. : N/A	From : Airport Pulling Road	
County : Collier	To : Heritage Trail	
No. of Lanes : 4 @ 12'	Beg M.P. : 0.990      End M.P. : 1.000	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves										% Bitumen
			FC2	S	---	---	---	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
1	1.100	R2	0.60	2.90	---	---	---	---	---	3.50	100.00	94.75	88.71	61.98	46.34	36.35	27.81	20.06	11.05	5.82	6.79
2	1.433	R1	0.60	2.60	---	---	---	---	---	3.20	100.00	91.87	85.22	58.19	43.04	33.64	25.88	18.84	10.25	5.31	7.26
5	2.432	R2	0.60	2.60	---	---	---	---	---	3.20	100.00	97.98	91.75	64.71	46.34	36.17	28.22	20.87	11.52	6.19	7.35
6	2.765	R1	0.50	2.80	---	---	---	---	---	3.30	100.00	95.48	90.13	67.28	50.39	39.29	30.39	22.01	11.53	5.91	7.33

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.