

Pavement Composition Data Sheet

Date: June 20, 2011

Milling Depth : 3.00 in.

Page: 1

F. P. N. : 414547-1-52-01	S.R. No.: 35	<u>Notes</u>
F. A. P. No. : N/A	From : DeSoto County Line	
County : Hardee	To : CR 634	
No. of Lanes : 2 @ 12'	Beg M.P. : 0.000 End M.P. : 5.030	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves										% Bitumen
			F125	S	T1	ST	---	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
1	0.500	R1	1.60	0.80	2.00	0.40	---	---	---	4.80	100.00	97.50	90.34	69.58	52.80	42.45	35.86	28.00	13.90	4.66	6.22
2	1.000	L1	1.50	1.10	2.80	0.60	---	---	---	6.00	100.00	99.02	94.99	70.45	51.66	41.85	35.90	27.91	13.90	5.17	6.21
4	2.000	L1	1.60	1.00	0.80	0.50	---	---	---	3.90	100.00	97.15	91.88	69.62	51.71	41.83	35.89	28.51	14.61	5.19	5.86
5	2.500	R1	1.50	0.70	2.60	---	---	---	---	4.80	100.00	98.66	91.46	69.48	51.82	41.20	34.66	30.75	14.51	5.84	5.95
8	4.000	L1	1.10	0.90	3.10	0.50	---	---	---	5.60	100.00	99.14	94.20	68.65	48.78	40.06	35.00	27.35	14.43	5.47	6.02
9	4.500	R1	1.50	1.20	1.50	0.60	---	---	---	4.80	100.00	99.10	93.12	71.65	52.76	42.45	36.45	29.04	15.59	5.78	6.04

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.