

### Pavement Composition Data Sheet

Date: May 17, 2011

Milling Depth : 3.00 in.

Page: 1

F. P. N. : 428904-1-52-01	C.R. No.: 675	<u>Notes</u>
F. A. P. No. : Arra 722 b	From : US 301	
County : Manatee	To : SR 64	
No. of Lanes : 2 @ 12'	Beg M.P. : 0.000      End M.P. : 9.493	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves										% Bitumen
			S	T1	---	---	---	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
1	0.500	R1	2.80	1.30	---	---	---	---	---	4.10	100.00	96.92	91.20	73.43	57.15	47.76	40.91	31.93	13.02	5.38	7.41
2	1.000	L1	1.80	2.40	---	---	---	---	---	4.20	100.00	99.04	96.77	82.17	69.18	59.14	50.44	38.13	14.83	5.00	7.78
5	4.000	R1	1.20	2.50	---	---	---	---	---	3.70	100.00	100.00	99.30	92.62	80.20	67.95	56.24	38.01	16.34	5.61	8.19
6	4.500	L1	0.90	3.20	---	---	---	---	---	4.10	100.00	99.82	99.68	95.09	83.43	69.07	56.41	38.35	16.27	5.32	8.25
9	6.000	R1	1.50	2.50	---	---	---	---	---	4.00	100.00	100.00	99.76	94.04	82.92	68.93	56.09	38.49	17.22	6.15	8.37
10	6.500	L1	1.80	4.00	---	---	---	---	---	5.80	100.00	99.34	98.66	91.46	78.82	64.34	51.73	35.36	16.27	6.57	7.90
13	8.000	R1	1.00	3.00	---	---	---	---	---	4.00	100.00	99.78	99.16	93.37	83.57	72.08	60.66	40.64	17.27	5.46	8.18
14	8.500	L1	1.80	10.00	---	---	---	---	---	11.80	100.00	100.00	100.00	96.26	84.88	69.63	55.61	36.75	16.14	6.11	8.11

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.