

### Pavement Composition Data Sheet

Date: July 20, 2011

Milling Depth : 1.50 in.

Page: 1

F. P. N. : 428743-1-52-01	S.R. No.: 79	<u>Notes</u>
F. A. P. No. : N/A	From : SR 30 (US 98A)	
County : Bay	To : SR 30 (US 98) PCB Parkway	
No. of Lanes : 2@12'	Beg M.P. : 0.020      End M.P. : 0.502	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves									% Bitumen	
			FC9.5	SP	SAHM	SAHM	ST	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100		No. 200
1	0.232	R1	0.90	1.20	3.40	---	---	---	---	5.50	100.00	99.70	98.26	74.34	53.03	40.13	32.26	20.24	7.63	6.56	5.79
2	0.232	R2	1.00	1.50	---	---	---	---	---	2.50	100.00	99.71	98.19	76.52	55.41	41.24	32.73	19.59	7.56	5.57	6.02
3	0.400	L1	1.30	1.50	5.00	7.50	0.50	---	---	15.80	100.00	100.00	96.80	76.11	54.73	40.55	32.24	20.62	8.05	5.79	5.81

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.