

Pavement Composition Data Sheet

Date: April 26, 2011

Milling Depth : 2.00 in.

Page: 1

F. P. N. : 426932-2-52-01	S.R. No.: 85	<u>Notes</u>
F. A. P. No. : N/A	From : North of SR 123	
County : Okaloosa	To : 0.5 mile North of SR 123	
No. of Lanes : 4 @ 12'	Beg M.P. : 4.088 End M.P. : 4.612	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves										% Bitumen
			FC5	12.5	S	---	---	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
1	4.210	R2	0.70	1.30	1.90	---	---	---	---	3.90	100.00	91.60	79.37	51.21	37.39	28.88	22.59	13.73	6.20	4.45	4.99
2	4.210	R3	0.80	1.50	---	---	---	---	---	2.30	99.31	93.67	81.61	48.24	28.30	26.32	20.60	12.59	6.19	4.57	5.28
3	4.100	L1	0.50	2.10	1.70	---	---	---	---	4.30	98.71	93.40	83.03	55.18	39.32	30.51	24.35	15.27	6.06	4.09	5.66

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.