

Pavement Composition Data Sheet

Date: July 29, 2011

Milling Depth : 2.75 in.

Page: 1

F. P. N. : 407951-3-52-01	S.R. No.: 50	<u>Notes</u>
F. A. P. No. : 3001 029 p	From : US 19	
County : Hernando	To : Mariner Boulevard	
No. of Lanes : 4@12'	Beg M.P. : 0.000 End M.P. : 3.870	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves										% Bitumen
			FC2	S	T1	---	---	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
2	1.729	L2	0.20	6.00	2.80	---	---	---	---	9.00	100.00	99.22	96.31	67.09	46.75	37.27	30.77	24.12	13.98	6.18	6.24
5	1.776	R2	0.60	3.80	---	---	---	---	---	4.40	100.00	99.18	96.02	65.94	45.98	36.83	30.80	24.12	14.09	6.90	6.02
6	3.408	R2	0.70	3.50	---	---	---	---	---	4.20	100.00	99.19	96.43	64.97	45.85	36.05	29.65	23.17	13.34	6.31	6.41
8	2.191	L1	0.60	5.70	1.30	---	---	---	---	7.60	100.00	100.00	95.09	67.94	50.64	40.39	33.01	25.83	15.18	7.16	5.97
9	0.485	L1	0.70	7.50	1.50	---	---	---	---	9.70	100.00	98.89	92.28	70.61	52.62	42.04	34.56	26.96	15.49	6.69	6.10
12	2.584	R1	0.40	3.80	---	---	---	---	---	4.20	100.00	99.53	98.00	75.99	56.77	45.15	37.30	29.13	16.62	8.42	6.50

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.