

Pavement Composition Data Sheet

Date: March 8, 2011

Milling Depth : 3.00 in.

Page: 1

F. P. N. : 427145-1-52-01	S.R. No.: 685	<u>Notes</u>
F. A. P. No. : N/A	From : E. Waters Ave.	
County : Hillsborough	To : E. Linebaugh Ave.	
No. of Lanes : 6 @ 12'	Beg M.P. : 5.360 End M.P. : 6.360	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves										% Bitumen
			FC2	S	T1	BIND	---	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
1	5.528	R3	0.50	1.50	---	1.20	---	---	---	3.20	97.20	90.82	84.35	63.03	49.59	41.90	36.76	27.49	12.62	5.40	6.67
2	5.694	R1	0.90	1.50	0.80	0.80	---	---	---	4.00	100.00	98.89	91.86	61.07	44.70	36.30	30.93	22.18	9.03	4.75	6.43
5	6.192	R3	0.70	1.50	0.80	0.60	---	---	---	3.60	100.00	98.76	90.08	64.43	50.28	40.66	34.59	25.02	10.34	6.06	6.78
6	6.325	R1	0.50	1.20	0.90	0.70	---	---	---	3.30	100.00	95.77	89.61	66.26	51.54	42.69	37.06	27.29	12.91	6.47	6.63
7	5.528	L3	0.40	1.30	1.00	1.00	---	---	---	3.70	100.00	98.61	93.59	70.58	54.65	45.33	39.57	29.90	14.89	9.44	6.49
8	5.694	L1	0.40	1.60	0.60	0.60	---	---	---	3.20	100.00	98.99	93.46	69.89	56.37	47.65	41.68	31.53	16.33	10.19	6.38
11	6.192	L3	0.40	1.50	0.80	0.60	---	---	---	3.30	100.00	99.79	93.24	67.96	51.10	40.76	34.51	24.87	10.50	5.55	6.76
12	6.325	L1	0.40	1.50	1.10	---	---	---	---	3.00	100.00	99.78	94.04	71.32	56.46	46.08	39.42	28.51	12.94	6.38	6.99

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.