

## Pavement Composition Data Sheet

Date: May 13, 2011

Milling Depth : 2.75 in.

Page: 1

F. P. N. : 427159-1-52-01	S.R. No.: 580	<u>Notes</u>
F. A. P. No. : N/A	From : W. of Benjamin Rd.	
County : Hillsborough	To : E. of Westshore Blvd.	
No. of Lanes : 6 @ 12'	Beg M.P. : 7.250      End M.P. : 8.440	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves										% Bitumen
			FC2	S	CRL	T1	---	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
1	7.300	R3	0.30	3.50	---	---	---	---	3.80	100.00	97.91	91.19	59.95	42.98	34.26	28.40	21.27	10.24	5.44	5.78	
5	8.181	R3	0.60	3.00	---	---	---	---	3.60	100.00	98.54	92.00	58.96	42.56	35.50	30.31	23.29	10.83	5.27	5.65	
6	8.287	R1	0.60	7.40	---	---	---	---	8.00	100.00	98.15	92.58	62.55	45.00	37.02	31.50	24.31	11.22	6.03	6.13	
7	7.380	L3	0.70	3.70	0.50	---	---	---	4.90	100.00	97.98	89.09	57.50	43.45	34.47	28.32	20.77	8.84	4.87	5.70	
8	7.516	L1	0.40	3.30	---	---	---	---	3.70	100.00	97.53	91.67	57.66	41.11	33.71	28.51	21.47	9.80	5.22	5.46	
11	8.164	L3	0.50	4.20	0.50	2.00	---	---	7.20	100.00	97.20	93.62	63.26	45.84	37.25	31.20	23.19	9.52	4.86	5.76	
12	7.300	L1	0.60	3.00	---	---	---	---	3.60	100.00	98.08	92.40	59.00	42.30	34.63	29.23	21.93	9.96	5.04	5.30	
13	7.300	OR	0.50	2.10	---	---	---	---	2.60	100.00	96.80	92.50	62.55	45.47	36.58	30.67	22.88	9.83	5.13	5.75	

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.