

## Pavement Composition Data Sheet

Date: September 10, 2012

Milling Depth : 3.00 in.

Page: 1

F. P. N. : 429077-2-52-01	S.R. No.: 582 (Fowler Ave.)	<u>Notes</u>
F. A. P. No. : None	From : West of Nebraska Ave.	
County : Hillborough	To : West of Bruce B. Downs Blvd.	
No. of Lanes : 8 @ 12	Beg M.P. : 0.489      End M.P. : 2.000	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves										% Bitumen
			FC2	S	T1	BIND	---	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
1	0.550	R4	0.50	3.30	---	---	---	---	---	3.80	100.00	98.22	92.69	63.08	48.11	38.71	33.24	24.48	8.67	5.13	6.51
2	0.692	R3	0.50	3.40	---	---	---	---	---	3.90	100.00	97.40	84.98	56.55	44.68	37.94	33.14	25.44	10.34	5.39	6.26
5	1.118	R4	0.60	2.90	---	---	---	---	---	3.50	100.00	98.12	88.90	55.89	43.18	36.29	31.76	24.40	9.35	4.58	6.05
6	1.260	R3	0.70	3.10	---	---	---	---	---	3.80	100.00	97.86	90.27	58.49	45.38	38.78	34.17	26.53	10.49	5.16	6.03
7	1.402	R2	0.50	3.30	---	---	---	---	---	3.80	100.00	98.53	90.17	61.90	46.65	38.32	32.92	24.69	9.91	5.38	6.82
10	0.692	L3	0.70	2.70	---	---	---	---	---	3.40	100.00	98.79	92.45	58.52	43.26	35.57	30.91	23.88	9.81	4.77	6.86
11	0.834	L2	0.50	3.50	7.00	1.10	---	---	---	12.10	100.00	98.23	91.41	63.55	47.03	38.51	33.28	26.23	11.08	5.80	6.49
12	0.932	L1	0.50	3.40	---	---	---	---	---	3.90	100.00	99.56	91.77	61.87	46.29	37.35	31.80	24.39	9.83	4.87	6.32
14	1.260	L3	0.50	3.40	---	---	---	---	---	3.90	100.00	99.62	91.49	63.32	47.29	38.28	32.90	25.57	10.84	5.99	6.49
16	1.569	L1	0.40	2.70	1.00	---	---	---	---	4.10	100.00	99.24	92.95	64.53	48.46	40.42	35.02	26.73	10.95	6.75	6.58

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.