

### Pavement Composition Data Sheet

Date: September 5, 2012

Milling Depth : 4.00 in.

Page: 1

F. P. N. : 409154-1-52-01	S.R. No.: 688 (Ulmerton Road)	<u>Notes</u>
F. A. P. No. : 1394 026 u	From : East of Wild Acres Road	
County : Pinellas	To : El Centro/Ranchero Boulevards	
No. of Lanes : 4 @ 12'	Beg M.P. : 6.570      End M.P. : 7.460	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves										% Bitumen
			FC4	S	T1	BIND	---	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
1	6.616	R2	0.50	1.50	0.70	1.20	---	---	---	3.90	100.00	98.27	91.30	72.43	56.12	43.31	33.52	24.22	11.33	5.33	7.67
2	6.923	R1	0.30	1.50	---	1.80	---	---	---	3.60	100.00	97.69	93.07	73.19	56.06	43.28	34.41	24.97	10.57	5.10	7.27
4	7.310	R1	0.90	0.80	1.00	2.20	---	---	---	4.90	100.00	93.94	91.14	72.16	56.97	46.20	34.53	22.98	10.46	5.46	6.71
5	6.590	L1	0.60	1.00	1.00	1.60	---	---	---	4.20	100.00	97.42	93.01	70.53	54.52	42.80	32.82	22.69	9.49	5.44	7.03
6	6.826	L1	0.50	1.00	1.20	1.20	---	---	---	3.90	100.00	95.75	89.55	68.28	52.54	40.95	32.11	22.44	9.45	5.37	6.96
8	7.277	L1	0.70	1.40	---	1.60	---	---	---	3.70	100.00	96.08	92.01	74.42	58.71	45.41	33.59	22.09	9.73	5.03	7.00

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.