

## Pavement Composition Data Sheet

Date: May 10, 2012

Milling Depth : 2.50 in.

Page: 1

F. P. N. : 429056-1-52-01	S.R. No.: 60	<u>Notes</u>
F. A. P. No. : N/A	From : W. of Chestnut Street	
County : Pinellas	To : End of Memorial Bridge	
No. of Lanes : 4 @ 11'	Beg M.P. : 0.000      End M.P. : 0.760	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves										% Bitumen
			FC6	S	T1	ST	---	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
1	0.076	L4	1.50	---	5.60	0.50	---	---	---	7.60	100.00	98.47	93.33	74.45	55.94	45.18	37.94	28.70	12.65	5.49	6.58
2	0.146	L3	1.40	---	3.70	0.80	---	---	---	5.90	100.00	98.68	92.22	77.43	62.50	48.00	38.21	29.08	14.62	6.50	6.52
3	0.272	L2	1.10	---	4.00	---	---	---	---	5.10	100.00	100.00	98.78	81.86	63.07	46.25	35.46	25.98	13.57	5.94	7.06
4	0.184	L1	1.50	---	1.30	---	---	---	---	2.80	100.00	98.31	94.22	74.73	54.83	44.31	37.91	29.53	11.45	5.83	6.21

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.

## Pavement Composition Data Sheet

Date: May 10, 2012

Milling Depth : 2.50 in.

Page: 2

F. P. N. : 429056-1-52-01	S.R. No.: 60	<u>Notes</u>
F. A. P. No. : N/A	From : E. of Palm Avenue	
County : Pinellas	To : W. of Court Street	
No. of Lanes : 4 @ 11'	Beg M.P. : 0.900      End M.P. : 1.400	

Core No.	M.P.	Lane	Pavement Layers (in.)							Core Length (in.)	Percent Passing Sieves										% Bitumen
			FC6	S	T1	ST	---	---	---		3/4 in.	1/2 in.	3/8 in.	No. 4	No. 8	No. 16	No. 30	No. 50	No. 100	No. 200	
1	0.900	R2	1.70	1.50	---	---	---	---	---	3.20	100.00	97.31	91.36	71.18	55.99	42.81	33.52	23.75	10.32	5.98	6.79
3	1.022	R3	1.10	1.50	2.80	---	---	---	---	5.40	100.00	97.64	91.62	73.18	57.43	47.18	39.66	30.69	12.50	6.80	6.93
7	1.393	R2	1.50	---	8.00	---	---	---	---	9.50	100.00	97.23	94.20	76.24	60.83	49.19	40.88	31.35	12.73	6.82	6.27

Please note that these roadway core test results are for informational purposes only and are not to be considered as a guarantee of the pavement composition other than at the locations identified in this summary.