

EXPECTED IMPLEMENTATION JANUARY 2017

916 BITUMINOUS MATERIALS. (REV 5-6-16) (FA 6-20-16) (1-17)

ARTICLE 916-2.1 is deleted and the following substituted:

916-2.1 Requirements: Superpave Performance Graded (PG) asphalt binders, identified as PG 52-28, PG 58-22, PG 67-22, polymer modified asphalt (PMA) binders, PG 76-22 (PMA) and PG 82-22 (PMA), and asphalt rubber binders (ARB), PG 76-22 (ARB), shall meet the requirements of 916-2 and AASHTO M 332-14. When the Contract Documents specify either a PG 76-22 (PMA), PG 76-22 (ARB), or PG 76-22 binder, either binder can be used interchangeably at no additional cost to the Department. All PG asphalt binders shall meet the following additional requirements:

1. The intermediate test temperature at 10 rad/sec. for the Dynamic Shear Rheometer (DSR) test (AASHTO T 315-12) shall be 26.5°C for PG grades PG 67 and higher.
2. An additional high temperature grade of PG 67 is added for which the high test temperature at 10 rad/sec for the DSR test (AASHTO T 315-12) shall be 67°C.
3. All PG asphalt binders having a high temperature designation of PG 67 or lower shall be prepared without modification.
4. All PMA binders having a high temperature designation higher than PG 67 shall only be produced with a styrene-butadiene-styrene (SBS) or styrene-butadiene (SB) elastomeric polymer modifier and the resultant binder shall meet all requirements of this Section.
5. Polyphosphoric acid may be used as a modifier not exceeding 0.75% by weight of asphalt binder for PG 76-22 (PMA), PG 76-22 (ARB), and PG 82-22 (PMA) binders.
6. PG 76-22 (ARB) shall meet the additional requirements of 916-2.1.1.
7. All PG asphalt binders having a high temperature designation of PG 67 or lower shall not have a high temperature true grade more than 5.9°C higher than the specified PG grade, (for example, if a PG 58-22 is specified, do not supply a PG 64-22 or higher).
8. The use of waste oil is prohibited in the modification of any PG binder grade. Waste oil shall be defined as recycled oil products that have not been processed through a vacuum tower and have an initial boiling point of 385°C (725°F) or lower when tested in accordance with ASTM D6352.

For all PG binder used in all hot mix asphalt, silicone may be added to the PG binder at the rate of 25 cubic centimeters of silicone mixed to each 5,000 gallons of PG binder. If a disbursing fluid is used in conjunction with the silicone, the resultant mixture containing the full 25 cubic centimeters of silicone shall be added in accordance with the manufacturer's recommendation. The blending of the silicone with the PG binder shall be done by the supplier prior to the shipment. When the asphalt binder will be used with a foaming warm mix technology, refer to the technology supplier's guidance on the addition of silicone.

Where an anti-strip additive is required, the anti-strip additive shall meet the requirements of 916-4. The anti-strip additive shall be introduced into the PG binder by the supplier during loading.

916-2.1.1 Additional Requirements for PG 76-22 (ARB): The following additional requirements apply only to PG 76-22 (ARB):

1. The asphalt binder shall contain a minimum of 7.0% ground tire rubber (GTR) by weight of asphalt binder.
2. The GTR shall meet the requirements of Section 919.

EXPECTED IMPLEMENTATION JANUARY 2017

3. Polymer modification is optional for PG 76-22 (ARB).

4. Use of excess PG 76-22 (ARB): The Contractor may use excess PG 76-22 (ARB) in other asphalt concrete mixes requiring the use of a PG 67-22 binder by blending with straight PG 67-22 binder so that the total amount of ground tire rubber in the binder is less than 2.0%. The Contractor may use excess PG 76-22 (ARB) in asphalt concrete mixtures requiring the use of a PG 52-28 or PG 58-22 by blending with the designated binder in such proportions that the total amount of ground tire rubber in the binder is less than 1.0%.

916-2.2 Compliance with Materials Manual: Producers of Superpave PG binders shall meet the requirements of Section 3.5, Volume II of the Department's Material Manual, which may be viewed at the following URL:

<http://www.dot.state.fl.us/programmanagement/Implemented/URLinSpecs/Section35V2.shtm>.

916-2.3 Reporting: Specification compliance testing results shall be reported for the tests in the table below, unless noted otherwise. Quality control (QC) testing results shall be reported for original binder DSR ($G/\sin \delta$ and phase angle, as applicable).

| SUPERPAVE PG ASPHALT BINDER | | |
|--|---|---|
| Test and Method | Conditions | Specification Minimum/Maximum Value |
| Superpave PG Asphalt Binder Grade | | Report |
| APL Number | | Report |
| Modifier (name and type) | Polymer, Ground Tire Rubber with Approved Product List (APL) number, Sulfur, PPA, REOB, and any Rejuvenating Agents | Report |
| Original Binder | | |
| Solubility, AASHTO T 44-14 | in Trichloroethylene | Minimum 99.0% (Not applicable for PG 76-22 (ARB)) |
| Flash Point, AASHTO T 48-06 (2015) | Cleveland Open Cup | Minimum 450°F |
| Rotational Viscosity, AASHTO T 316-13 | 275°F | Maximum 3 Pa·s ^(a) |
| Dynamic Shear Rheometer ^(b) , AASHTO T 315-12 | $G^*/\sin \delta$ | Minimum 1.00 kPa |
| | Phase Angle, δ ^(c) PG 76-22 (PMA) and PG 76-22 (ARB) ^(d) PG 82-22 (PMA) | Maximum 75 degrees Maximum 65 degrees |
| Separation Test, ASTM D 7173-14 and Softening Point, AASHTO T 53-09 (2013) | 163±5°C | Maximum 15°F (PG 76-22 (ARB) only) |
| | 48 hours | |
| Rolling Thin Film Oven Test Residue (AASHTO T 240-09) | | |

D

R

A

F

T

EXPECTED IMPLEMENTATION JANUARY 2017

D

R

A

| | | |
|--|--|---|
| Rolling Thin Film Oven, AASHTO T 240-13 | Mass Change % | Maximum 1.00 |
| Multiple Stress Creep Recovery, $J_{nr, 3.2}$ AASHTO M 332-14 | Grade Temperature (Unmodified binders only) | "S" = 4.50 kPa^{-1} max |
| Multiple Stress Creep Recovery, $J_{nr, 3.2}^{(d, e, f)}$ AASHTO M 332-14 | 67°C (Modified binders only) | "V" = 1.0 kPa^{-1} max "E" = 0.5 kPa^{-1} max Maximum $J_{nr, diff} = 75\%$ |
| Multiple Stress Creep Recovery, %Recovery ^(d, e) AASHTO M 332-14 | 67°C (Modified binders only) | $\%R_{3.2} \geq 29.37$ $(J_{nr, 3.2})^{-0.2633}$ |
| Pressure Aging Vessel Residue (AASHTO R 28-12) | | |
| Dynamic Shear Rheometer, AASHTO T 315-12 | $G^* \sin \delta$, 10 rad/sec. | Maximum 5000 kPa ^(f, g) |
| Creep Stiffness, AASHTO T 313-12 | S (Stiffness), @ 60 sec. m-value, @ 60 sec. | Maximum 300 MPa Minimum 0.300 |
| <p>(a) Binders with values higher than 3 Pa·s should be used with caution and only after consulting with the supplier as to any special handling procedures, including pumping capabilities.</p> <p>(b) Dynamic Shear Rheometer (AASHTO T 315) shall be performed on original binders for the purposes of QC testing only.</p> <p>(c) The original binder phase angle (AASHTO T 315-12) shall be performed at grade temperature.</p> <p>(d) AASHTO T 315-12 and AASHTO T 350-14 will be performed at a 2 mm gap for PG 76-22 (ARB)</p> <p>(e) All binders with a high temperature designation >67 will be tested at 67°C. PG 76-22 (PMA) and PG 76-22 (ARB) shall pass a "V" graded and PG 82-22 (PMA) shall pass an "E" grade per AASHTO M 332-14.</p> <p>(f) A maximum $J_{nr, diff} = 75\%$ does not apply for any J_{nr} value $\leq 0.5 \text{ kPa}^{-1}$.</p> <p>(g) For all PG grades of a PG 67 or higher, perform the PAV residue testing at 26.5°C with a maximum of 5000 kPa.</p> | | |

SUBARTICLE 916-3.1 is deleted and the following substituted:

916-3.1 Compliance with Materials Manual: Producers of asphalt emulsions shall meet the requirements of Section 3.4, Volume II of the Department's Material Manual, which may be viewed at the following URL:

<http://www.dot.state.fl.us/programmanagement/Implemented/URLinSpecs/Section34V2.shtm>.

ARTICLE 916-4 is deleted and the following substituted:

916-4 Liquid Anti-strip Agents.

916-4.1 Requirements: Liquid anti-strip agents shall be tested in accordance with FM 1-T 283. A minimum tensile strength ratio of 0.80 must be obtained when testing the liquid anti-strip with various aggregate sources and two nominal maximum aggregate size mixtures for approval to be placed on the APL.

916-4.2 Mix Design Verification: Particular aggregate sources may require moisture susceptibility testing per FM 1-T 283 for each mix design. Results from this testing may meet the Department's requirement of minimum tensile strength ratio of 0.80 or may indicate the need for a larger dosage rate of anti-strip agent (up to 0.75% maximum) or may require a different anti-strip agent to meet the specification requirements.

F

T