

EXPECTED IMPLEMENTATION JULY 2014

160 STABILIZING. (REV 11-4-13) (FA 11-15-13) (7-14)

SUBARTICLE 160-3.1 is deleted and the following substituted:

160-3.1 General: Prior to the beginning of stabilizing operations, construct the area to be stabilized to an elevation such that, upon completion of stabilizing operations, the completed stabilized subgrade will conform to the lines, grades, and cross-section shown in the Plans. Prior to spreading any additive stabilizing material, bring the surface of the roadbed to a plane approximately parallel to the plane of the proposed finished surface.

Construct mainline pavement lanes, turn lanes, ramps, parking lots, concrete box culverts and retaining wall systems meeting the requirements of 120-8.1, except replace “Embankment” with “Subgrade”.

Construct shoulder-only areas, sidewalk, and shared use path areas meeting the requirements of 120-8.1 except replace “Embankment” with “Subgrade” and meet the acceptance criteria of 160-4.2.

Isolated mixing operations will be considered as separate LOTS. Curbpads and shoulders compacted separately shall be considered separate LOTS. Isolated compaction operations will be considered as separate LOTS. For multiple phase construction, a LOT shall not extend beyond the limits of the phase.

SUBARTICLE 160-4.2.4 is deleted and the following substituted:

160-4.2.4 Frequency: Conduct QC sampling and testing at a minimum frequency listed in the table below. The Engineer will perform Verification sampling and tests at a minimum frequency listed in the table below.

Test Name	Quality Control	Verification	Verification for Shoulder-Only, Shared Use Path and Sidewalk Construction
Modified Proctor Maximum Density	One per two consecutive LOTS	One per eight consecutive LOTS	One per four LOTS
Density	One per LOT	One per four LOTS	One per two LOTS
Stabilizing Mixing Depth	Three per 500 feet	Witness one per LOT	Witness one per LOT
LBR	One per two consecutive LOTS	One per eight consecutive LOTS	One per four LOTS
Gradation, LL/PI & Soil Classification (Local materials)	Not Required	One per eight consecutive LOTS	One per four LOTS