

# EXPECTED IMPLEMENTATION JULY 2014

## **450 PRECAST PRESTRESSED CONCRETE CONSTRUCTION.** **(REV 12-16-13) (FA 1-28-14) (7-14)**

SUBARTICLE 450-12.5.3 is expanded by the following:

### **450-12.5.3.7: Pretensioned Concrete Poles:**

Longitudinal cracks: The length of each crack must be less than twice the base width of the pole.

Transverse or diagonal cracks: Cracks perpendicular to or at an inclined angle to the longitudinal direction of the pole. The length of each crack must be less than two-thirds of the base width of the pole.

Edge cracks: Cracks exhibiting at the edge and extending across one or two adjacent planes of a square pole. The total length of each crack must be less than 2.0 inches.