

EXPECTED IMPLEMENTATION JULY 2014

548 RETAINING WALL SYSTEMS. (REV 1-16-14) (FA 1-22-14) (7-14)

SUBARTICLE 548-2.6.2 is deleted and the following substituted:

548-2.6.2 Compacted Select Backfill: Meet the requirements of Sections 105 and 120 except as noted within this Section. Have the backfill material tested for every soil type for pH, resistivity, sulfate and chloride content by a Department approved independent testing laboratory prior to placement. Provide certification to the Engineer that the results have met the requirements of this Section and are signed and sealed by a Professional Engineer, registered in the State of Florida.

The pH, as determined by FM 5-550, shall not be lower than 5.0 and not higher than 9.0. Sources of select backfill material having a pH between 4.5 and 5.0 for walls utilizing metallic reinforcement and between 3.0 and 5.0 for walls utilizing geosynthetic reinforcement with no metallic elements or pipes placed within the backfill, as determined by FM 5-550, may be used provided the interior face of the MSE wall panels have 3 inches of concrete cover over the reinforcement and the concrete used in the panels contains the following ingredients and proportions:

1. The quantity of cement replaced with Type F fly ash is 10% to 20% by weight.
2. The quantity of cement replaced with slag is 50% to 60% by weight.
3. Portland cement is 30% by weight of total cementitious material.
4. The total weight of the Type F fly ash and slag does not exceed 70% of total cementitious material.

In lieu of the mix design described above, a mix design with a fast pozzolanic material meeting the requirements of 346-2.3(6) silica fume, metakaolin and ultrafine fly ash, can be substituted. Examples of mix designs meeting this requirement are:

1. 8% silica fume plus 20% fly ash
2. 10% metakaolin plus 20% fly ash

Provide proper curing for these materials to prevent surface cracking.

Do not place metallic pipe in backfill materials having a pH less than 5.0.

Use backfill for walls using soil reinforcements that meets the following gradation limits determined in accordance with AASHTO T27 and FM 1-T011:

In addition, for permanent walls utilizing metallic soil reinforcement, use backfill that meets the following electro-chemical test criteria for determining corrosiveness:

Criteria	Test Method
Resistivity: > 3000 ohm -·cm	FM 5-551
Soluble sulfate content: < 200 PPM	FM 5-553
Soluble chloride content < 100 PPM	FM 5-552

EXPECTED IMPLEMENTATION JULY 2014

For walls not using soil reinforcement, use backfill that meets the following gradation limits determined in accordance with AASHTO T27 and FM 1-T011:

Sieve Size	Percent Passing
3-1/2 inches	100
No. 200	0-12

D

R

A

F

T