

STATEWIDE CRITICAL REQUIREMENT LIST – FISCAL YEAR 2018/2019
Quality Assessment Category Number 7B
Asphalt Milling & Paving

1. A string line is being used for an accurate, uniform alignment of the pavement edge in areas where there is no curb and gutter. The deviation along the unsupported pavement edge shall be not more than +/- 1.5 inches from the stringline. [Spec. 330-6.1.1]
2. Do not allow the mixture to adhere to the wheels or tires of any rollers and do not use fuel or other petroleum distillates to prevent adhesion. Scrapers, pads, and moistening systems shall be functioning properly to avoid having HMA adhering to the wheels. [Spec. 330-5.3.3]
3. Do not dump embankment or base material directly on the pavement. Dress shoulders before placing the friction course on adjacent pavement. [Spec.120-12.2 and 330-10]
4. Texture of the Finished Surface of Pavement Layers: Produce a finished surface of uniform texture and compaction with no pulled, torn, crushed, raveled, or loosened portions and free of segregation, bleeding, flushing, sand steaks, sand spots, or ripples. Address any pavement not meeting the requirements of this specification in accordance with 330-9.5. [Spec. 330-9.2]

Quality Assessment Category Number 7B
Asphalt Milling & Paving