PAVEMENT EVALUATION CORING AND CONDITION DATA
INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
06	447802-1-52-01	01	THE CONTROL CARD IS CORRECT

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ: 447802-1-52-01
TYP SECT: 01

FA PROJ:
COUNTY: MIAMI-DADE
SR NUMBER: SR 5

MEDIAN:
CURBED: NO

NAME: SR-5 / US-1
FROM: SOUTH OF SW 232 ST.
TO: SOUTH OF SW 112 AVE/

BEG MP: 9.73
END MP: 11.97 LENGTH: 2.24

PROJECT MEASUREMENT: ENGLISH

CORED BY: TERRACON
DATE: 2022-03-03
LANES: 4 @ FEET

SHOULDER TYPE
INSIDE:
OUTSIDE:

CURB & GUTTER: NO

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE NO.	MILE POST	VFY	LN	W P	--TOP	PAVEMENT LAYER					CORE LNGTH	BASE	SUB	CRACK DEPTH	CRACK TYP	CRACK CLSS	CRACK EXT	PMT CND	COMMENTS
					F125	S1	S1	S1	S1	S1		LR	ST40						
1	9.821	N	L2	Y	1.00	1.00	2.00	1.50	1.80	2.80	10.10	12.0	12.0					F	SG:LT BROWN LR W/SAND
2	10.047	N	OT	Y	1.30	1.30					2.60	24.0						F	SG:LT BROWN LR W/SAND
3	10.874	N	L1	Y	.90	1.00	2.00	1.80	1.40	2.00	9.10	12.0	12.0					F	SG:LT BROWN LR W/SAND
4	11.024	N	L2	Y	1.00	1.00	1.80	1.80	1.00	8.90	15.50	12.0	12.0					F	SG:LT BROWN LR W/SAND
5	11.064	N	R1	Y	1.30	1.50	1.00	1.00	2.50	4.30	11.60	24.0						F	SG:LT BROWN LR W/SAND
6	11.292	N	R2	Y	1.30	1.50	1.30	1.00	1.80	1.80	8.70	24.0						F	SG:LT BROWN LR W/SAND
7	11.723	N	R1	Y	1.00	1.00	2.00	1.50	2.00	2.00	9.50	18.0	6.0					F	SG:LT BROWN LR W/SAND
8	11.808	N	OT	Y	1.50						1.50	12.0	12.0					F	SG:LT BROWN LR W/SAND
9	11.835	N	R2	Y	.80	.80	1.50	.80	1.30		5.20	24.0						F	SG:LT BROWN LR W/SAND
10	11.255	N	L1	Y	1.30	1.00	1.60	1.00	2.10	2.50	9.50	12.0	12.0					F	SG:LT BROWN LR W/SAND
	.000																		

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ	
1	MILLING RECOMMENDATIONS: MILL 1.5 INCHES AND
2	REPAVE 1.5 INCHES WITH FC-12.5

CODE DESCRIPTIONS

CRACK TYPE	TYPE DESCRIPTION
A	ALLIGATORING IN WHEELPATH
B	BLOCK CRACKING
C	COMBINATION OF TYPES

CRACK EXTNT	EXTENT DESCRIPTION
L	LIGHT
M	MEDIUM
S	SEVERE

CRACK CLASS	CLASS DESCRIPTION
IB	UNKNOWN
II	UNKNOWN
III	UNKNOWN

CODE DESCRIPTIONS

SURFACE LAYER CODE	DESCRIPTION
ARMI	ASPHALT RUBBER MEMBRANE INTERL
BIND	ASPHALT BINDER COURSE
BRCK	BRICK PAVERS
CONC	PORTLAND CEMENT CONCRETE
CRL	CRACK RELIEF LAYER
FAB	PAVEMENT OVERLAY FABRIC
FC	FRICTION COURSE
FC1	FRICTION COURSE 1
FC2	FRICTION COURSE 2
FC3	FRICTION COURSE 3
FC4	FRICTION COURSE 4
FC5	FRICTION COURSE 5
FC5B	FRICTION COURSE 5 BONDED
FC6	FRICTION COURSE 6
F12M	FRIC. COURSE 12.5 MODIFIED
F125	FRICTION COURSE 12.5
F95	FRICTION COURSE 9.5
F95M	FRIC. COURSE 9.5 MODIFIED
S	TYPE S ASPHALTIC CONCRETE
SAHM	SAND ASPHALT HOT MIX
SP1C	9.5 SUPERPAVE COARSE GRADED
SP1F	9.5 SUPERPAVE FINE GRADED
SP2C	12.5 SUPERPAVE COARSE GRADED
SP2F	12.5 SUPERPAVE FINE GRADED
SP3C	19.0 SUPERPAVE COARSE GRADED
SP3F	19.0 SUPERPAVE FINE GRADED
ST	SURFACE TREATMENT
S1	TYPE S-I ASPHALTIC CONCRETE
S2	TYPE S-II ASPHALTIC CONCRETE
S3	TYPE S-III ASPHALTIC CONCRETE
T1	TYPE I ASPHALTIC CONCRETE
T2	TYPE II ASPHALTIC CONCRETE
T3	TYPE III ASPHALTIC CONCRETE
UNIM	UNIMPROVED SURFACE
UNKW	UNKNOWN
WC	WEARING COURSE
WC1	WEARING COURSE 1
WC2	WEARING COURSE 2
WC3	WEARING COURSE 3
WC4	WEARING COURSE 4
WC5	WEARING COURSE 5
WC6	WEARING COURSE 6
WC7	WEARING COURSE 7
WC8	WEARING COURSE 8